

TEFROLITH® FTG-20



Insulating Ship-Floor for A-class 30 divisions Insulating mortar-system also for wet areas, requires a weight distribution layer as final layer which is approved as not readily ignitable

Properties:

- non-combustible, A-30 rating, (min. 20 mm)
- low weight
- not self-levelling, formation of slope possible

Preparation of Substructure:

Anchoring clips on deck required!

All deck areas have to be treated with a stable 2 comp. EP-shopprimer fast to saponification, which has to be treated with one coat, TEFROTEX® SF BONDING COAT.

Other deck types upon request.

Technical Data:

Installation thickness: FTG-20 Insulating coat: min. approx. 20 mm (A-30) Density: FTG-20 Insulating coat: approx. 0,80 kg/ m²/ mm

Strengths:

TEFROLITH® FTG-20 insulating coatmeasurements based on 4 x 4 x 16 cm prisms -
after 28 days:
compressive strength:approx. 7 N/ mm²
approx. 7 N/ mm²tensile strength:approx. 2 N/ mm²

Fire Rating:

TEFROLITH® FTG-20 complies with FTP-Code Part 3.

Issued: 30 July 2012, Revision 2.0

GLC

© 2006



G. Theodor Freese GmbH & Co. KG Carl-Benz-Straße 29 28237 Bremen ☎ +49 (421) 396 08-0
≞ +49 (421) 396 08-399

contact@gtf-freese.de
 http://www.gtf-freese.de