

TEFROKA® EP Coating



**Ship-deck-covering, 2-component epoxy resin system
solvent-free, for using of final surface floor coverings**

Properties:

- joint less
- very fast curing
- abrasion-resistant
- excellent adhesion to pre-treated deck coverings type **TEFROTEX®**
- antislip
- withstands salt solutions, thinned mineral acids/ lyes, petrol, mineral oil and grease
- open for foot traffic after 15 hours
- several colours/designs

Preparation of Substructure:

Deck coverings have to be dry, clean and free from foreign matters.

Primering with **TEFROKA® EP**.

Technical Data:

Thickness of coat: 2 - 10 mm * *

Density (+20° C): approx. 1,7 kg/ m²/ mm

Solid state by volume: approx. 100 %

Fire rating:

TEFROKA® EP Coating complies with FTP-Code Part 5.

* (approved thickness may vary)

* If applied in multiple coats higher thickness is possible

Issued: 30 July 2012, Revision 2.0

