

TEFROKA® PU-E COMFORT T



**Elastic polyurethane system, solvent-free
for interior decks onboard cruise liners, yachts, ferries, balconies etc.
for installation of elastic final surfaces**

Properties:

- one layer, joint less
- very good noise reduction
- watertight
- high point load resistance
- abrasion-resistant
- anti slip
- decorative surface design
- several colours/designs
- self-levelling

Preparation of Substructure:

Filling of dents with either 2-comp. polyurethane material, e.g. **TEFROKA® PU-1-L** or cementous approved **TEFROTEx®**-primary deck coverings

Technical Data:

Thickness:	2-15 mm * *
Density:	approx. 1,3 kg/ m ² / mm
Viscosity (+20°C):	self levelling
Solid body:	100 %
Pot Life (+20°C):	approx. 30 minutes
Drying (+20°C / humidity 65%):	
Open for foot traffic:	approx. 15 hours
Ready for service:	approx. 7 days
Time interval for following layers (+20°C):	
	min. 15 hours
	max. 48 hours
Shore-D-hardness:	approx. 35

Fire Rating:

TEFROKA® PU-E COMFORT T complies with FTP-Code Part 5.

* (approved thickness may vary)

* If applied in multiple coats higher thickness is possible

Issued: 30 July 2012, Revision 2.0

