

## TEFROTEX® 500



**Primary Deck-Covering**  
**Spot levelling below carpet**  
**Using in wet areas upon request**

### Properties:

- extremely low weight
- very good adhesion to steel- and pre-treated aluminium galvanized deck surfaces
- open for foot traffic after 4 hours (20° C)
- one component
- easy application

### Preparation of Substructure:

All deck areas have to be treated with a stable shopprimer. For partial levelling application can be made directly, for application for the whole area pre-treatment of one coat **TEFROTEX® SF BONDING COAT** should be done.

Other deck types upon request.

### Technical Data:

Standard thickness:	1,0 – 30 mm *
Density:	approx. 0,55 kg/ m <sup>2</sup> / mm
Strengths:	On 4 x 4 x 16 cm prisms – after 28 days
compressive strength:	approx. 6,0 N/ mm <sup>2</sup>
tensile-strength:	approx. 2,5 N/ mm <sup>2</sup>

### Fire Rating:

**TEFROTEX® 500** complies with FTP-Code Part 6.

\* (approved thickness may vary)

Issued: 30 July 2012, Revision 2.0

