

# TEFROTEX® 60-L



## Primary Deck-Covering

**Underlay for floor coverings in accommodation,  
also for wet areas and ceramic tiles**

### Properties:

- low weight
- not self levelling, forming of slope is possible
- good adhesion to pre-treated steel-, aluminium and galvanized deck surfaces
- open for foot traffic after approx. 16 hours (20° C)
- water-resistant
- one coat, joint less
- not readily ignitable

### Preparation of Substructure:

All deck areas have to be treated with a stable intact 2 comp- EP-shopprimer fast to saponification, which has to be treated with one coat **TEFROTEX® SF BONDING COAT**.

Other deck types upon request.

### Technical Data:

|                       |   |
|-----------------------|---|
| Thickness:            | 8 - 40 mm * *   |
| Density:              | approx. 0,95 kg/ m <sup>2</sup> / mm                          |
| Strengths:            | measurements based on 4 x 4 x 16 cm prisms -<br>after 28 days |
| compressive strength: | approx. 18 N/ mm <sup>2</sup>                                 |
| tensile strength:     | approx. 5 N/ mm <sup>2</sup>                                  |

### Fire Rating:

**TEFROTEX® 60-L** complies with FTP-Code Part 6

\* (approved thickness may vary)

\* If applied in multiple coats higher thickness is possible

Issued: 30 July 2012, Revision 2.0

