

TEFROTEX® 90-L

Primary Deck-Covering

**Subfloor for carpets and elastic coverings in accommodation,
using in wet areas upon request**

Properties:

- self levelling
- one component
- very good adhesion to pre-treated steel-, aluminium and galvanized deck surfaces,
- open for foot traffic after 3 hours (20° C).
- very low weight
- easy mixing and application
- application by pump is possible

Preparation of Substructure:

All deck areas have to be treated with a shopprimer, which has to be treated with one coat **TEFROTEX® SF BONDING COAT**.
Other deck types and levelling of dents upon request.

Technical Data:

Thickness:	0,5 - 50 mm *
Density:	approx. 0,9 kg/ m ² / mm
Strengths:	
	measurements based on 4 x 4 x 16 cm prisms - after 28 days
compressive strength:	approx. 15 N/ mm ²
tensile strength:	approx. 4 N/ mm ²

Fire Rating:

TEFROTEX® 90-L complies with
FTP-Code Part 5 and Part 6.

* (approved thickness may vary)

Issued: 30 July 2012, Revision 2.0

