

TEFROTEX® SF



Primary Deck-Covering

**Underlay for floor coverings in accommodation,
not for wet areas**

Properties:

- one coat, joint less
- self-levelling
- very good adhesion to pre-treated steel-, aluminium and galvanized deck surfaces
- high surface strength
- very fast, almost tension-free hardening
- high strength at an early stage
- open for foot traffic after 3 hours (20°C)
- ready for use after 12 hours (20°C)
- ready to obtain all kinds of floor coverings after 24 hours (20 °C)

These characteristics are independent of the thickness of coat laid.

Preparation of Substructure:

All deck areas have to be treated with a stable intact shopprimer, which has to be treated with one coat **TEFROTEX® SF BONDING COAT**.
Other deck types upon request.

Technical Data:

Thickness:	1 – 30 mm * *
Density:	approx. 1,8 kg/ m ² / mm
Strengths:	on 4 x 4 x 16 cm prisms - after 28 days
compressive strength:	approx. 30 N/ mm ²
tensile strength:	approx. 8 N/ mm ²

Approved according to FTPC Part 1 as part of an A-60-construction

thickness: approx. 2,0 kg/ m²/ mm (filled with quartzsand)

Strengths:	on 4 x 4 x 16 cm prisms - after 28 days
compressive strength:	approx. 26 N/ mm ²
tensile strength:	approx. 8 N/ mm ²

Fire Rating:

TEFROTEX® SF complies with FTP-Code Part 5 and Part 6.

* (approved thickness may vary)

* If applied in multiple coats higher thickness is possible

Issued: 30 July 2012, Revision 2.0

